



BallClay

BW7

Sio₂ : 60
Al₂O₃: 27
Fe₂O₃: 0.6
TiO₂: 0.3
CaO: 1.1
MgO: 0.4
Na₂O: 0.4
K₂O: 1.2
L.O.I: 9

Plasticity: 36
Firing shrinkage: 3
Moisture: 8
Brightness (1180c): 95
Physical Form : Noodled
Packking : Big Bag

Applicablity:
Glaze & Engob
Table Ware-body