




Kaolin

KW35

Sio2 : 57%
Al2O3: 31%
Fe2O3: 0.2%
TiO2: 0.3%
CaO: 0.6
MgO: 0.4
Na2O: 0.2
K2O: 0.3
L.O.I: 10

Plasticity: 34
Flexural Strength: 29
Firing shrinkage: 4
Drying shrinkage: 5
Moisture: 8
Brightness (1180c): 98
Physical Form : Noodled
Packing : Big Bag

Applicablity:
Glaze & Engob
Table Ware-body